

## Megaplast Textured Geomembrane (Double-Sided)

Megaplast High Density Polyethylene (HDPE) Geomembrane is manufactured with the highest quality resin specifically formulated and used in applications that require excellent chemical resistance and endurance properties.



## MEGAPLAST

### AT THE CORE:

An HDPE geomembrane suitable for applications that require excellent chemical resistance and endurance properties

## MEGAPLatinum TEXTURED D 300

### Technical Data Sheet

This product specifications meet or exceed GRI GM 13

Sr.No.	Properties	Test Method (ASTM)	Unit (English)	Testing Frequency	MEGAPLatinum TEXTURED D 300
1	Thickness - ((nom -5 %) min ave.) (Note7(a))	D 5994	mils	Every roll	120
	Lowest Individual for 8 out of 10 values (Note7(b))				108
	Lowest Individual reading for any of the 10 values (Note7(c))				102
2	Density (min ave)	D 792	g/cc	Every (200,000 lb)	0.940
3	<b>Tensile Properties (min.ave)</b> (Note6)	D 6693 Type IV Dumbell , 2ipm		Every 5th roll	
	→Break strength		lb/in		188
	→ Yield strength		lb/in		257
	→Break Elongation		G.L. 50mm		%
	→Yield Elongation	G.L. 33mm	%		12
4	Tear Resistance (min.ave)	D 1004	lb	Every 10th roll	84
5	Puncture Resistance (min ave)	D 4833	lb	Every 10th roll	185
6	Carbon Black Content (Range)	D 4218 / D 1603	%	Every 5th roll	2.0 - 3.0
7	Carbon Black Dispersion	D 5596	Category	Every 10th roll	Note 1
8	Asperity Height (min ave)	D 7466	mil	Every 2nd roll	Note 2
9	Stress Crack Resistance (Note 5) (SP - Notched Constant Tensile Load)	D 5397 (Appendix)	Hrs.	Each two resin lots (One lot = 200,000 lb)	500
10	Oxidative Induction Time (min.ave) Standard -OIT -- OR--- High Pressure -OIT	D 3895 ( at 200 dig C )	Minutes	Every 200,000 lb	> 100
		D 5885 ( at 150 dig C )			> 500
11	Oven Aging at 85 deg C. Standard -OIT ( min.ave) - % retained after 90 days --OR--- High Pressure -OIT ( min.ave) - % retained after 90 days	D 5721 D 3895	%	Per each formulation	55
		D 5721 D 5885			80
12	UV Resistance HP -OIT ( min.ave) - % retained after 1600 hrs	D 7238 D 5885	%	Per each formulation	50

Rev2. date : 14-05-2018

TYPICAL ROLL DIMENSIONS (Note3)		
Roll Width ,	feet	26.24
Roll Length ,	feet	190
Roll Area ,	Sq. Feet	4986

Note 1: Dispersion only applies to near spherical agglomerates 9 of 10 views shall be category 1 or 2 . No more than 1 view from category 3 .

Note 2: 16 mil average .

Note 3: Roll length & widths have a tolerance of +/- 1% .

Note 4: All geomembranes have dimensional stability of +/- 2% when tested according to ASTM D 1204 .

Note 5 : NCTL for HD textured is conducted on representative smooth membrane sample .

Note 6 : Machine direction(MD) & Cross direction (XMD) average values should be on the basis of 5 specimens each direction.

Note 7 : (a) Minimum average core thickness is - 5% of the nominal thickness.

(b) lowest thickness for 8 out of 10 values is - 10% of the nominal value .

(c) lowest thickness for any of the 10 values is -15% of the nominal value.