

Megaplast Smooth Geomembrane

Megaplast High Density Polyethylene (HDPE) Geomembrane is manufactured with the highest quality resin specifically formulated and used in applications that require excellent chemical resistance and endurance properties.



MEGAPLAST

AT THE CORE:

An HDPE geomembrane suitable for applications that require excellent chemical resistance and endurance properties

MEGAPLATINUM 300

Technical data Sheet

This product specifications meet or exceed GRI GM 13

Sr.No.	Properties	Test Method (ASTM)	Unit (English)	Testing Frequency	MEGAPLATINUM 300
1	Thickness - (min. ave)	D 5199	mils	Every roll	120
	Lowest Individual Reading of 10 values				108
2	Density (min. ave)	D 792	g/cc	Every 200,000 lb	0.940
3	Tensile Properties (min.ave) (Note4)	D 6693 Type IV Dumbell , 2ipm	lb/in	Every 5th roll	485
	→Break strength				257
	→ Yield strength	G.L. 50mm	%		700
	→Break Elongation		%		13
	→Yield Elongation	G.L. 33mm	%		
4	Tear Resistance (min.ave)	D 1004	lb	Every 10th roll	84
5	Puncture Resistance (min ave)	D 4833	lb	Every 10th roll	216
6	Carbon Black Content (Range)	D 4218 / D 1603	%	Every 5th roll	2.0 - 3.0
7	Carbon Black Dispersion	D 5596	Category	Every 10th roll	Note 1
8	Stress Crack Resistance (SP - Notched Constant Tensile Load)	D 5397 (Appendix)	Hrs.	Each two resign lots (One lot = 200,000 lb)	500
9	Oxidative Induction Time (min.ave) Standard -OIT	D 3895 (at 200 dig C)	Minutes	Every 200,000 lb	> 100
	-- OR--- High Pressure -OIT	D 5885 (at 150 dig C)			> 500
10	Oven Aging at 85 deg C. Standard -OIT (min.ave) - % retained after 90 days	D 5721 D 3895	%	Per each formulation	55
	---OR---- High Pressure -OIT (min.ave) - % retained after 90 days	D 5721 D 5885			80
11	UV Resistance HP -OIT (min.ave) - % retained after 1600 hrs	D 7238 D 5885	%	Per each formulation	50

Rev2. date: 14-05-2018

TYPICAL ROLL DIMENSIONS (Note2)	
Roll Width , feet	26.24
Roll Length , feet	230
Roll Area , Sq . Feet	6035

Note 1 : Dispersion only applies to near spherical agglomerates 9 of 10 views shall be category 1 or 2 . No more than 1 view from category 3 .

Note 2 : Roll length & widths have a tolerance of +/- 1% .

Note 3 : All geomembranes have dimensional stability of +/- 2% when tested according to ASTM D 1204 .

Note 4 : Machine direction(MD) & Cross direction (XMD) average values should be on the basis of 5 specimens each direction.