



# Megaplast Textured Geomembrane (Single-Sided)

Megaplast High Density Polyethylene (HDPE) Geomembrane is manufactured with the highest quality resin specifically formulated and used in applications that require excellent chemical resistance and endurance properties.

# MEGAPLAST

## AT THE CORE:

An HDPE geomembrane suitable for applications that require excellent chemical resistance and endurance properties

## MEGAGOLD PLUS TEXTURED S 200

### Technical Data Sheet

Sr.No.	Properties	Test Method (ASTM)	Unit (English)	Testing Frequency	MEGAGOLD PLUS TEXTURED S 200	
1	Thickness - ((nom -10 %) min ave.)	D 5994	mils	Every roll	80	
2	Density (min ave)	D 792	g/cc	Every 200,000 lb	0.940	
	Melt Flow Index (MFI) ( 190°C/2.16 kgf)	D 1238	g /10 min	Per batch / lot	≤ 1.0	
3	<b>Tensile Properties (min.ave)</b> (Note2)	D 6693 Type IV Dumbell , 2ipm		Every 5th roll		
	→Break strength		lb/in		120	
	→ Yield strength		lb/in		148	
	→Break Elongation		G.L. 50mm		%	150
	→Yield Elongation		G.L. 33mm		%	12
4	Tear Resistance (min.ave)	D 1004	lb	Every 10th roll	50	
5	Puncture Resistance (min ave)	D 4833	lb	Every 10th roll	108	
6	Carbon Black Content (Range)	D 4218 / D 1603	%	Every 5th roll	2.0 - 3.0	
7	Carbon Black Dispersion	D 5596	Category	Every 10th roll	Note 1	
8	Asperity Height (min ave )	D 7466	mils	Every 2nd roll	12	
9	Stress Crack Resistance (Note 5) (SP - Notched Constant Tensile Load )	D 5397 (Appendix)	Hrs.	Each two resign lots (One lot = 200,000 lb)	500	
10	Oxidative Induction Time (min.ave )	D 3895	Minutes	Every 200,000 lb	> 100	
	Standard -OIT	( at 200 dig C )				
	-- OR-- High Pressure -OIT	D 5885 ( at 150 dig C)			> 500	
11	Oven Aging at 85 deg C.	D 5721	%	Per each formulation	55	
	Standard -OIT ( min.ave) - % retained after 90 days	D 3895				
	---OR---	D 5721			80	
	High Pressure -OIT ( min.ave) - % retained after 90 days	D 5885				
12	UV Resistance HP -OIT ( min.ave) - % retained after 1600 hrs	D 7238 D 5885	%	Per each formulation	50	

Rev. date :  
Jan-2019

TYPICAL ROLL DIMENSIONS (Note3)		
Roll Width	feet	23.0
Roll Length	feet	260
Roll Area	Sq. Feet	5980

Note 1: Dispersion only applies to near spherical agglomerates 9 of 10 views shall be category 1 or 2 . No more than 1 view from category 3 .

Note 2: Machine direction(MD) & Cross direction (XMD) average values should be on the basis of 5 specimens each direction.

Note 3: Roll length & widths have a tolerance of +/- 1% .

Note 4: All geomembranes have dimensional stability of +/- 2% when tested according to ASTM D 1204 .

Note 5 : NCTL for HD textured is conducted on representative smooth membrane sample .

**H.O.:** 21-C, Mittal Towers, 2nd Floor, C-Wing, Nariman Point, Mumbai - 400 021, INDIA  
**Tel. No.:** +91-22-61066000 **Email:** geomembranes@megaplast.in **Website:** www.megaplast.in