

# Megaplast Smooth Geomembrane

Megaplast High Density Polyethylene (HDPE) Geomembrane is manufactured with the highest quality resin specifically formulated and used in applications that require excellent chemical resistance and endurance properties.



# MEGAPLAST

### AT THE CORE:

An HDPE geomembrane suitable for applications that require excellent chemical resistance and endurance properties

## MEGAPLATINUM 150 (Conductive)

### Technical data Sheet

This product specifications meet or exceed GRI GM 13

Sr.No.	Properties	Test Method (ASTM)	Unit (English)	Testing Frequency	MEGAPLATINUM 150 (Conductive)	
1	Thickness - (min. ave)	D 5199	mils	Every roll	60	
	Lowest Individual Reading of 10 values				54	
2	Density (min. ave)	D 792	g/cc	Every 200,000 lb	0.940	
3	<b>Tensile Properties (min.ave)</b> (Note4)	D 6693 Type IV Dumbell , 2ipm		Every 5th roll		
	→Break strength		lb/in		246	
	→ Yield strength		lb/in		130	
	→Break Elongation		G.L. 50mm		%	700
	→Yield Elongation		G.L. 33mm		%	13
4	Tear Resistance (min.ave)	D 1004	lbs	Every 10th roll	42	
5	Puncture Resistance (min ave)	D 4833	lbs	Every 10th roll	112	
6	Carbon Black Content (Range) (Only Nonconductive Layer)	D 4218 / D 1603	%	Every 5th roll	2.0 - 3.0	
7	Carbon Black Dispersion	D 5596	Category	Every 10th roll	Note 1	
8	Stress Crack Resistance (SP - Notched Constant Tensile Load )	D 5397 (Appendix)	Hrs.	Each two resign lots (One lot =200,000 lb)	500	
9	Oxidative Induction Time (min.ave) Standard -OIT	D 3895 ( at 200 dig C )	Minutes	Every 200,000 lb	> 100	
	-- OR--- High Pressure -OIT	D 5885 ( at 150 dig C )			> 500	
10	Oven Aging at 85 deg C. Standard -OIT ( min.ave) - % retained after 90 days	D 5721 D 3895	%	Per each formulation	55	
	---OR---- High Pressure -OIT ( min.ave) - % retained after 90 days	D 5721 D 5885			80	
11	UV Resistance HP -OIT ( min.ave) - % retained after 1600 hrs	D 7238 D 5885	%	Per each formulation	50	
12	Application (Note 5)				Conductive	

### TYPICAL ROLL DIMENSIONS (Note2)

Roll Width ,	feet	23.5
Roll Length ,	feet	460
Roll Area ,	Sq. feet	10810

Note 1 : Dispersion only applies to near spherical agglomerates 9 of 10 views shall be category 1 or 2 . No more than 1 view from category 3 .

Note 2 : Roll length & widths have a tolerance of +/- 1% .

Note 3 : All geomembranes have dimensional stability of +/- 2% when tested according to ASTM D 1204 .

Note 4 : Machine direction(MD) & Cross direction (XMD) average values should be on the basis of 5 specimens each direction.

Note 5 : **The conductive layer may cause the carbon black content results to be higher than 3% .**

H.O.: 21-C, Mittal Towers, 2nd Floor, C-Wing, Nariman Point, Mumbai - 400 021, INDIA  
Tel. No.: +91-22-61066000 Email: geomembranes@megaplast.in Website: www.megaplast.in

Rev. date :  
07-07-2020